




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	Parafon® Step for Grids
Suspension Height:	w = 50

Octave band (Hz)	Sound absorption coefficient (-)
63	0
125	0.15
250	0.5
500	0.95
1000	1
2000	1
4000	1
α_w	0.80
NRC	0.85



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 17-322-M17	2017-12-15

