




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	Parafon® Step for Grids
Suspension Height:	w = 700

Octave band (Hz)	Sound absorption coefficient (-)
63	0.25
125	0.5
250	0.65
500	0.9
1000	0.95
2000	1
4000	1
α_w	0.90
NRC	0.90



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 17-322-M21	2017-12-15

