




# SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

|                   |                            |          |        |
|-------------------|----------------------------|----------|--------|
| <b>Client:</b>    | Boom Interior              |          |        |
| <b>Object:</b>    | Xrozz Absorption Ovan Bord |          |        |
| <b>Size [mm]:</b> | w = 450                    | h = 1800 | d = 40 |

| Octave band (Hz)             | Equivalent sound absorption area / unit (m <sup>2</sup> Sabine) |
|------------------------------|---|
| 63                           | 0.25  |
| 125                          | 0.35  |
| 250                          | 0.57  |
| 500                          | 0.72  |
| 1000                         | 0.82  |
| 2000                         | 1.01  |
| 4000                         | 1.25  |
| <b>N<sub>10</sub> = 13.9</b> |   |



| ORIGINAL TEST REPORTS            | DATE OF REPORT |
|----------------------------------|----------------|
| Akustikverkstan report 20-240-M2 | 2020-06-24     |
| Akustikverkstan report 18-701-M3 | 2018-08-23     |

The presented results are interpolated using the method described in ISO 20189 from the original test reports.

