




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 40 mm
Suspension Height:	w = 0

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.15
250	0.55
500	1
1000	1
2000	1
4000	1
α_w	0,85(H)
NRC	0.90



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 14-83-M13	2014-06-30

