




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive A 40 mm
<b>Suspension Height:</b>	w = 100

Octave band (Hz)	Sound absorption coefficient (-)
63	0.1
125	0.3
250	0.75
500	1
1000	1
2000	1
4000	1
$\alpha_w$	1,00
NRC	0.95



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 14-83-M15	2014-06-30

