


SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 40 mm
Suspension Height:	w = 200

Octave band (Hz)	Sound absorption coefficient (-)
63	0.15
125	0.45
250	0.9
500	1
1000	1
2000	1
4000	1
α_w	1,0
NRC	1.00



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 14-83-M16	2014-06-30

