




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive A 40 mm
<b>Suspension Height:</b>	w = 400

Octave band (Hz)	Sound absorption coefficient (-)
63	0.25
125	0.6
250	0.75
500	0.9
1000	1
2000	1
4000	1
$\alpha_w$	0.95
NRC	0.90



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 14-83-M17	2014-06-30

