


# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive D2 25 mm
<b>Suspension Height:</b>	w = 50

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.15
250	0.6
500	0.95
1000	0.9
2000	0.9
4000	1
$\alpha_w$	0.90
NRC	0.85



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 16-051-M68	2016-03-09

