




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive D2 25 mm
<b>Suspension Height:</b>	w = 200

Octave band (Hz)	Sound absorption coefficient (-)
63	0.15
125	0.55
250	0.7
500	0.85
1000	0.85
2000	1
4000	1
$\alpha_w$	0.90
NRC	0.85



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 16-051-M70a	2016-03-09

