




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive D2 25 mm
Suspension Height:	w = 400

Octave band (Hz)	Sound absorption coefficient (-)
63	0.15
125	0.5
250	0.6
500	0.7
1000	0.85
2000	0.9
4000	1
α_w	0,80(H)
NRC	0.75



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 16-051-M71	2016-03-09

