




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

| | |
|---------------------------|---------------------------|
| Client: | Parafon |
| Surface: | PARAFON Exclusive A 18 mm |
| Suspension Height: | w = 0 |

| Octave band (Hz) | Sound absorption coefficient (-) |
|------------------|----------------------------------|
| 63 | 0 |
| 125 | 0.05 |
| 250 | 0.1 |
| 500 | 0.45 |
| 1000 | 0.8 |
| 2000 | 0.95 |
| 4000 | 1 |
| α_w | 0,40(MH) |
| NRC | 0.60 |



| | |
|-----------------------------------|-----------------------|
| ORIGINAL TEST REPORT | DATE OF REPORT |
| Akustikverkstan report 10-55-M143 | 2010-11-19 |

