




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 18 mm
Suspension Height:	w = 0

Octave band (Hz)	Sound absorption coefficient (-)
63	0
125	0.05
250	0.1
500	0.45
1000	0.8
2000	0.95
4000	1
α_w	0,40(MH)
NRC	0.60



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 10-55-M143	2010-11-19

