




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 18 mm
Suspension Height:	w = 50

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.1
250	0.35
500	0.8
1000	1
2000	1
4000	1
α_w	0,65(MH)
NRC	0.80



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 10-55-M144	2010-11-19

