




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 18 mm
Suspension Height:	w = 100

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.15
250	0.55
500	0.95
1000	1
2000	0.95
4000	1
α_w	0,85(H)
NRC	0.85



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 10-55-M145	2010-11-19

