




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 18 mm
Suspension Height:	w = 200

Octave band (Hz)	Sound absorption coefficient (-)
63	0.15
125	0.4
250	0.75
500	0.95
1000	0.9
2000	0.95
4000	1
α_w	0.95
NRC	0.90



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 10-55-M146	2010-11-19

