




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	PARAFON Exclusive A 18 mm
Suspension Height:	w = 700

Octave band (Hz)	Sound absorption coefficient (-)
63	0.4
125	0.5
250	0.55
500	0.75
1000	0.9
2000	0.95
4000	1
α_w	0,80(H)
NRC	0.80



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 10-55-M148	2010-11-19

