




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client: Blå Station
Surface: Gaia Surface

Octave band (Hz)	Sound absorption coefficient (-)
63	0
125	0.05
250	0.35
500	0.7
1000	0.85
2000	0.85
4000	0.9
α_w	0.65(H)
NRC	0.70



ORIGINAL TEST REPORT

16-165-M1

DATE OF REPORT

2016-07-13

