




SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

Client:	Götessons/ Gotessons, Akustikmiljö / Am Acoustics		
Object:	Effekt		
Size [mm]:	w = 1200	h = 600	d = 50

Octave band (Hz)	Equivalent sound absorption area / unit (m ² Sabine)
63	0.2
125	0.4
250	0.8
500	1.2
1000	1.4
2000	1.4
4000	1.5
N₁₀ = 8.3	



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 16-239-M11	2017-03-09

