




SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

Client:	Götessons/ Gotessons, Akustikmiljö / Am Acoustics		
Object:	Effekt		
Size [mm]:	w = 1200	h = 900	d = 50

Octave band (Hz)	Equivalent sound absorption area / unit (m ² Sabine)
63	0.3
125	0.6
250	1.2
500	1.7
1000	2.1
2000	2.1
4000	2.3
N₁₀ = 5.9	



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 16-239-M12	2017-03-09

