




# SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

<b>Client:</b>	Akustikmiljö / Am Acoustics		
<b>Object:</b>	Single		
<b>Size [mm]:</b>	w = 1200	h = 900	d = 50

Octave band (Hz)	Equivalent sound absorption area / unit (m <sup>2</sup> Sabine)
63	0.1
125	0.34
250	0.76
500	1.2
1000	1.33
2000	1.1
4000	1.04
<b>N<sub>10</sub> = 9.6</b>	



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 16-239-M4	2016-11-25

