




SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

| | | | |
|-------------------|----------------------|----------|--------|
| Client: | Götessons/ Gotessons | | |
| Object: | ScreenIT A30 | | |
| Size [mm]: | w = 1400 | h = 1400 | d = 40 |

| Octave band (Hz) | Equivalent sound absorption area / unit (m ² Sabine) |
|---------------------------|---|
| 63 | 0.46 |
| 125 | 0.65 |
| 250 | 1.4 |
| 500 | 2 |
| 1000 | 2.5 |
| 2000 | 2.8 |
| 4000 | 2.9 |
| N₁₀ = 5 | |



| | |
|------------------------------------|-----------------------|
| ORIGINAL TEST REPORT | DATE OF REPORT |
| Akustikverkstan report 2629-R4-M19 | 2023-03-22 |

