




# SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

<b>Client:</b>	Abstracta		
<b>Object:</b>	Soneo Wall		
<b>Size [mm]:</b>	w = 1000	h = 1000	d = 30

Octave band (Hz)	Equivalent sound absorption area / unit (m <sup>2</sup> Sabine)
63	0.01
125	0.14
250	0.12
500	0.25
1000	0.32
2000	0.34
4000	0.37
<b>N<sub>10</sub> = 40</b>	



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 17-360-M6	2018-01-16

