


**SOUND ABSORPTION AREA FOR OBJECT**

Measured and evaluated according to SS-EN ISO 354 and SS 25269

CLIENT:	ABSTRACTA
OBJECT:	Combo Cross (Hanging Panel)
Size [mm]:	w = 1200    h = 2100    t = 14

1/3 octave band (Hz)	Equivalent sound absorption area / unit (m <sup>2</sup> Sabine)	
	1/3 octave band	Octave band
50	0,17	
63	0,28	0,3
80	0,33	
100	0,59	
125	0,64	0,7
160	0,80	
200	1,24	
250	1,42	1,5
315	1,75	
400	2,17	
500	2,27	2,3
630	2,39	
800	2,61	
1000	3,05	3,0
1250	3,20	
1600	3,33	
2000	3,96	3,9
2500	4,26	
3150	4,40	
4000	4,76	4,7
5000	4,94	
<i>N</i> <sub>10</sub> =	4,3	



**CONDITIONS**

Date of test:	2017-05-10	Object area:	2,5	m <sup>2</sup>
Date:	2017-05-22	Rev. room volume:	200	m <sup>3</sup>

Test report: **Akustikverkstan report 17-094-M10**  
 Signature: Delphine Bard